


PB P3 - 22 mm
Artikel: 14211, 10201

| | |
|---|--------------------------------------|
|  1393 | |
| KRONOSPAN CR spol. r. o., Na hranici 6, 586 01 Jihlava 10 | |
| P3-CPR-2013-07-01 | |
| EN 13 986 : 2004+A12015 EN 312 PB P3, 22 mm | |
| Reakce na oheň / Reaction to fire : | D-s2, d0 |
| Propustnost vodní páry / Water vapour permeability: | vlhká $\mu = 15$ suchá $\mu = 50$ |
| Únik formaldehydu / Release of formaldehyde: | E1 |
| Obsah pentachlorofenolu / Content of pentachlorophenol: | PCP ≤ 5 ppm |
| Vzduchová neprůzvučnost / Airborne sound insulation: | R = 29 dB |
| Zvuková pohltivost / Sound absorption: | $\alpha = 0,10 / 0,25$ |
| Tepelná vodivost / Thermal conductivity: | $\lambda = 0,13$ W / m . K |
| Trvanlivost / Durability as: | |
| - Rozlupčivost / Internal bond: | P3 |
| - Tloušťkové bobtnání / Swelling in thickness: | P3 |
| - Odolnost proti vlhkosti / Moisture resistance: | P3 |
| - Biologická trvanlivost / Biological (EN 335-3) : | Třída 2 / Class 2 |