

# Statement of the testing undertaken on behalf of Kronospan Limited

by

Microbiological Solutions Limited (MSL)  
Gollinrod, Walmersley, Bury, BL9 5NB, UK

Customer: Kronospan limited  
Contact name: Richard Milligan,  
Email: r.milligan@kronospan.co.uk

## Summary of testing

Testing was carried out according to **ISO 21702:2019** on the Laminate products on behalf of Kronospan Limited under Job reference **J003150**. Testing was carried out using a contact time **2-hour contact time** against H1N1, Human coronavirus 229E and RSV.

## Summary of Results

Job reference	Material	Organism	log reduction	Percentage reduction %
J3150	Melamine faced Medium density fibreboard	H1N1	0.83	85.21
	Melamine faced Medium density fibreboard	Human Coronavirus 229E	0.50	68.38
	Melamine faced Medium density fibreboard	RSV	0.22	39.74

Statement produced by:



Peter Thistlethwaite  
Technical Projects Manager

Date: 11/03/2022

Testing and report done by:



Megan Barrett  
Laboratory Manager

Date 11/03/2022